

Stick electrode

Features: ■ Applicable for 304 type steel


Classification: AWS A5.4 E308-16

Redrying Conditions: 150~200°Cx0.5~1h

Identification color: 1st Yellow

Polarity: AC, DCEP

Welding Positions:



Packaging data

φ mm	Length mm	kg/pack	kg/carton	g/piece	carton mm
2.0	250	2	20	11	300W, 125H, 280L
2.6	300	2	20	20	300W, 95H, 330L
3.2	350	5	20	36	175W, 115H, 380L
4.0	350	5	20	55	175W, 115H, 380L
5.0	350	5	20	82	175W, 115H, 380L

Composition (all-weld metal mass%)

	Typical (AC)	Guaranty ^a
C	0.06	0.08
Si	0.37	1.00
Mn	1.5	0.5~2.5
P	0.03	0.04
S	<0.01	0.03
Ni	9.4	9.0~11.0
Cr	20.0	18.0~21.0
Mo	0.16	0.75
Cu	0.08	0.75

Note: ^aSingle values are maximum.

Welding parameters (A)

φ mm	1F, 1G, 2F, 2G	3G uphill, 4G
2.0	50~75	45~65
2.6	75~95	70~90
3.2	85~120	80~115
4.0	110~160	90~140
5.0	150~200	-

All-weld mechanical properties

	Typical (AC)	Guaranty
0.2%YS (MPa)	410	-
TS (MPa)	600	552min.
El on 4d (%)	46	30min.
IV 0°C (J)	74	-

Approvals

ABS	MG (AWS A5.4 E308-16)
DNV-GL	VL308
NK^{a)}	KD308

Note: ^{a)} AC